



CERTIFICATE


Japanese Patent Application No.2002-184193 filed on
June 25, 2002

I, Hiroyuki Iida, of No.302, 1-10, Higashi 4-Chome, Kunitachi-Shi, Tokyo, 186-0002 Japan hereby declare that I am the translator of the documents attached and certify that the following is to the best of my knowledge and belief a true and correct translation.

Signed at 3rd day of April, 2006

A handwritten signature in cursive script, appearing to read "Hiroyuki Iida", written over a horizontal line.

Hiroyuki Iida



PATENT OFFICE
JAPANESE GOVERNMENT

This is to certify that the annexed is a true copy of the following application as filed with this Office.

Date of Application: June 25, 2002
Application Number: Patent Application No. 2002-184193
Applicant(s): FUJI PHOTO FILM CO., LTD.

May 6, 2003

Commissioner,
Patent Office

Shinichiro OHTA



Japanese Patent Application Number 2002-184193

Case Number: FJ2002-172

Filing Date: June 25, 2002

[Title of the Document]	Patent Application
[Reference Number]	FJ2002-172
[Filing Date]	June 25, 2002
[Destination]	Commissioner of the Patent Office
[International Patent Classification]	G11B 5/84
[Inventor]	
[Address or Domicile]	c/o FUJI PHOTO FILM CO., LTD., 12-1, Ohgi-cho 2-chome, Odawara-shi, Kanagawa
[Name]	Koji NAOE
[Applicant]	
[Identification Number]	000005201
[Name or Designation]	FUJI PHOTO FILM CO., LTD.
[Agent]	
[Identification Number]	100083116
[Patent Attorney]	
[Name or Designation]	Kenzo MATSUURA
[Indication of Official Fee]	
[Deposit Account Number]	012678
[Amount of the Fee]	21,000 yen
[List of Submitted Articles]	
[Title of Submitted Article]	Specification: 1
[Title of Submitted Article]	Drawings: 1
[Title of Submitted Article]	Abstract: 1
[General Authorization Number]	9801416
[Necessity of Proofreading]	Yes



Japanese Patent Application Number 2002-184193

Case Number: FJ 2002-172

Filing Date: June 25, 2002

[Title of the Document] Specification

[Title of the Invention] METHOD FOR PRODUCING MAGNETIC RECORDING
MEDIUM

[Claims for the Patent]

5 [Claim 1]

A method for producing a magnetic recording medium having a nonmagnetic substrate coated with a magnetic coating material containing a ferromagnetic powder and a binder, wherein:

10 the magnetic coating material contains a liquid A constituted by the ferromagnetic powder and a solvent, and a solution B of the binder; and

the liquid A and the solution B are mixed together by applying an ultrasonic wave thereto, and are thereafter subjected to dispersion processing.

[Detailed Description of the Invention]

[0001]

15 [Field of the Invention]

The present invention relates to a method for producing a magnetic recording medium, and particularly to a method for producing a low-noise and high-density coating-type magnetic recording medium.

[0002]

20 [Prior Art]

For increasing the density of the magnetic recording medium, the method of increasing the tape length (reducing the tape thickness) to increase the volume recording density, and the method of reducing the track width to increase the area recording density have been generally used in many systems as for tape-shaped media.

25 [0003]

Consequently, the reduced tape thickness has caused the problem of insufficient edge strength of tapes, thus bringing about a situation in which substrates of materials that have higher strength and are more expensive than conventional products must be used. Also, a servo technique has been developed for accommodating the recently adopted method of
30 reducing the track width, but this technique is difficult to apply particularly in a linear-type system, and the cost of development is considerably be increased.

[0004]

Methods other than those described above include the method of increasing the linear recording density as a method for increasing the density, but this method has been avoided because of the considerable reduction in C/N (carrier output/noise ratio) associated with short-wave recording.

5 [0005]

[Problems to be Solved by the Invention]

Recently, an increasing number of systems have adopted high-sensitivity MR heads as playback heads as a method for increasing the density. In this case, reduction of the medium noise and extreme reduction in thickness of the magnetic layer are required for the
10 magnetic recording medium. It can be considered that a finely granulated and uniformly distributed magnetic material is used, and the magnetic material is uniformly dispersed in preparation of a liquid as the method for reducing the medium noise.

[0006]

In the conventional liquid preparation method, however, the initial contact of the
15 magnetic material with a binder is achieved by a kneader or the like. In this case, since the coagulated magnetic material powder and the solution containing a high concentration of binder are mixed with a high shear force applied thereto, there arise problems such that the wettability of the magnetic material is reduced and hence the dispersibility of the magnetic material is compromised, and the coagulation of the magnetic material formed by kneading
20 cannot be dispersed after it is dispersed, if a magnetic material of fine particles is used. Also, there is a problem that the coagulation of the magnetic material causes not only a noise source but also defects such as seams in coating of an extremely thin magnetic layer.

[0007]

The object of the present invention is to solve the above problems of the prior art and
25 provide a low-noise high-density coating-type magnetic recording medium.

[0008]

[Means for Solving the Problems]

In order to attain the above-described object, the present invention is directed to a method for producing a magnetic recording medium having a nonmagnetic substrate coated
30 with a magnetic coating material containing a ferromagnetic powder and a binder, wherein: the magnetic coating material contains a liquid A constituted by the ferromagnetic powder and a solvent, and a solution B of the binder; and the liquid A and the solution B are mixed together

by applying an ultrasonic wave thereto, and are thereafter subjected to dispersion processing.

[0009]

According to the present invention, since the liquid A constituted by a ferromagnetic powder and a solvent can be mixed with the solution B of binder by applying the ultrasonic wave thereto, coagulated particles of the ferromagnetic powder can be dispersed and the coagulation of the ferromagnetic powder can be prevented, thus making it possible to obtain a liquid of ferromagnetic powder with uniform adsorption of the binder. As a result, a magnetic coating material suitable for a low-noise high-density coating-type magnetic recording medium is obtained.

[0010]

That is, as the particle size of the magnetic material decreases, the surface area of the magnetic material increases. Consequently, the ferromagnetic powder more likely coagulates when the raw material is prepared. The coagulated magnetic material has air trapped therein, but it is difficult to remove the air instantaneously when it initially contacts the binder solution because the magnetic material has a large surface area, and thus the surface of the magnetic material is not sufficiently wetted.

[0011]

Generally, there is the method in which by granulation such as compaction, deaeration in the powder is promoted to improve the wettability at the time of contact with the solution, but the method has a disadvantage that compaction with a fine particle magnetic material causes coagulation that is difficult to dispersed in the subsequent processing of dispersion of the magnetic coating material.

[0012]

According to the method for preparation of the magnetic coating material of the present invention, both the dispersing of coagulation of the ferromagnetic powder and the uniform mixing of the ferromagnetic powder and the binder can be performed at a time by cavitation of the ultrasonic wave, thus making it possible to create a state in which the size of secondary coagulation is reduced, and the binder is uniformly absorbed on the surface of the magnetic material. As a result, a magnetic coating material such that the amount of coagulated mass occurring after dispersion processing is not significant, and no magnetic materials are bound together magnetically can be prepared.

[0013]

In the present invention, it is preferable that the ultrasonic wave is applied within one second after the liquid A and the solution B are mixed together. If the ultrasonic wave is applied within a predetermined amount of time after the liquid A and the solution B are mixed together in this way, the above effect can be achieved more efficiently.

5 [0014]

Furthermore, it is preferable that the time until the ultrasonic wave is applied after the liquid A and the solution B are mixed together is within 5 seconds at the maximum. If a larger amount of time passes after the liquid A and the solution B are mixed together, a binder may be adsorbed on the surface of the coagulated ferromagnetic powder, and this situation
10 should be prevented.

[0015]

Also, in the present invention, it is preferable that the liquid A is subjected to dispersion processing by applying an ultrasonic wave thereto before the liquid A and the solution B are mixed together. If the liquid A is subjected to dispersion processing before the
15 liquid A and the solution B are mixed together in this way, the effect of the present invention can be exhibited more reliably.

[0016]

Also, in the present invention, it is preferable that the mixing of the liquid A and the solution B by application of the ultrasonic wave is carried out by a flow-type ultrasonic
20 dispersion apparatus. This is because, if the flow-type ultrasonic dispersion apparatus is used in this way, the effect of the present invention can be achieved more reliably.

[0017]

[Embodiments of the Invention]

A preferred embodiment of a production apparatus 10 for a magnetic coating material
25 for use in a method for producing a magnetic recording medium according to the present invention will be described below based on the accompanying drawings. Figure 1 is an overall block diagram of the production apparatus 10 for the magnetic coating material, and Figure 2 is a detailed sectional view of an ultrasonic dispersion apparatus 40 for use in an ultrasonic dispersion system 16.

30 [0018]

The production apparatus 10 for the magnetic coating material is constituted by a liquid A supplying system 12, a solution B supplying system 14, the ultrasonic dispersion

system 16, a sand mill dispersion system 18 and a magnetic coating solution preparing system 20 in this order from the upstream. Furthermore, the liquid A supplying system 12 and the solution B supplying system 14 are placed side by side, and are arranged so that they join into one just before the ultrasonic dispersion system 16.

5 [0019]

The liquid A supplying system 12 for supplying the liquid A and the solution B supplying system 14 for supplying the solution B are each constituted by a liquid tank, a liquid supplying device and the like. Specifically, the liquid A supplying system 12 is constituted by a liquid tank 21, a stirrer 22 with its leading end placed in the liquid tank 21, and a liquid
10 supplying pipe 23 from the liquid tank 21 and a liquid supplying pump 24. Similarly, the solution B supplying system 14 is constituted by a liquid tank 25, a stirrer 26 with its leading end placed in the liquid tank 25, a liquid supplying pipe 27 from the liquid tank 25 and a liquid supplying pump 28.

[0020]

15 For various kinds of constituent members for use in the liquid A supplying system 12 and the solution B supplying system 14 described above, a various kinds of well known members may be used. However, materials causing no contamination and corrosion are preferably employed in consideration of the nature specific to the magnetic coating material for the magnetic recording medium.

20 [0021]

In the ultrasonic dispersion system 16, three flow-type ultrasonic dispersion apparatuses 40, 60 and 62 are placed in series. For these three apparatuses, apparatuses of the same specifications are used. These ultrasonic dispersion apparatuses 40, 60 and 62 each have a configuration such that a liquid is supplied from the bottom face of the apparatus, and
25 the liquid is discharged from the side face of the apparatus. By placing three ultrasonic dispersion apparatuses 40, 60 and 62 in series in this way, coagulated particles of the ferromagnetic particle can reliably be dispersed, and the ferromagnetic powder and the binder can be mixed uniformly.

[0022]

30 In Figure 2, a liquid tank 42 of the ultrasonic dispersion apparatus 40 is a cylindrical container, and a straight part (liquid supplying part) 32 of an inverted Y type pipe 30 is connected to the lower end of the cylindrical container. A pipe 38 (liquid discharging part) is

connected to the upper part of the side face at one point. The inverted Y type pipe 30 has its leading end bifurcated, and a pipe 34 for the liquid A and a pipe 36 for the solution B joint into the straight part 32.

[0023]

By providing such the inverted Y type pipe structure, the liquid A and the solution B flow into the liquid tank 42 of the ultrasonic dispersion apparatus 40 to be exposed to an ultrasonic wave within a predetermined amount of time after they are mixed together. Thus, as long as the same effect can be exhibited, a same function can be obtained even if an inverted T type pipe or lateral T type pipe is used in place of the inverted Y type pipe 30.

[0024]

The upper end of the liquid tank 42 of the ultrasonic dispersion apparatus 40 is blocked by a flange 50 of an oscillator 44 described later to form a closed container. The cylindrical oscillator 44 is placed in the liquid tank 42 so that an ultrasonic wave can be applied to a liquid passing through the inside of the liquid tank 42. Furthermore, the flange 50 is combined with the oscillator 44 as one united body.

[0025]

A converter 46 is fixed to the upper end of the oscillator 44, and electricity is supplied to the converter 46 from a power supply 48. Hence, if the ultrasonic dispersion apparatus 40 is activated, ultrasonic vibrations are promoted by the converter 46, and an ultrasonic wave is applied to the inside of the liquid tank 42 by the oscillator 44.

[0026]

In the ultrasonic dispersion apparatus 40 of this structure, the space between the upper end of the oscillator 44 and the bottom face of the liquid tank 42 is 3 mm. In the ultrasonic dispersion apparatus 40 of this structure, the area where an ultrasonic wave is effectively applied is a nearly conic zone 52 (hatched area in Figure 2) below the lower end of the oscillator 44, and other zones are much inferior to the zone 52 in the effect of the ultrasonic wave.

[0027]

As described previously, the ultrasonic dispersion apparatuses 60 and 62 are placed one after another in the downstream of the ultrasonic dispersion apparatus 40. The ultrasonic dispersion apparatuses 60 and 62 each have the same structure as that of the ultrasonic dispersion apparatus 40 as described previously, and therefore the description thereof is not

presented. However, they differ from the ultrasonic dispersion apparatus 40 in that the pipes connected to the ultrasonic dispersion apparatuses 60 and 62 on the upstream side are straight pipes.

[0028]

5 For the flow-type ultrasonic dispersion apparatuses 40, 60 and 62 described above, for example, Flow-type Ultrasonic Dispersion Apparatus (trade name: US-1200TCVP) manufactured by Nihon Seiki Co., Ltd. can be used. For the specifications of this apparatus, the frequency is 20 kHz, the MAX amplitude is 30 μm , the rated output is 1200 W, the space between an irradiation part and a holder is 3 mm, and so on.

10 [0029]

Also, the inner diameters on inlet and outlet sides of the ultrasonic dispersion apparatuses 40, 60 and 62 are each 14 mm, and the pipe volume of the straight part of the inverted Y type pipe 30 (extending from the mixing part of the liquid A and the solution B to the inlet of the liquid tank 42) is 3 cm^3 .

15 [0030]

In Figure 1, the sand mill dispersion system 18 placed in the downstream of the ultrasonic dispersion system 16 is constituted by a liquid tank 70, a stirrer 72 with its leading end placed in the liquid tank 70, a liquid supplying pipe 74 from the liquid tank 70 and a liquid supplying pump 76, a sand mill dispersion apparatus 78, and a return pipe 80 from the sand mill dispersion apparatus 78 to the liquid tank 70.

[0031]

In this sand mill dispersion system 18, a liquid flowing from the ultrasonic dispersion system 16 is repeatedly circulated by the sand mill dispersion apparatus 78, and a part thereof is supplied to the magnetic coating solution preparing system 20 in the downstream.

25 [0032]

This sand mill dispersion system 18 is intended for further dispersing the ferromagnetic powder of the mixture of the liquid A and the solution B, and for various kinds of constituent members for use in the system, various kinds of well known members may be used. However, materials causing no contamination and corrosion are preferably employed in consideration of the nature specific to the magnetic coating material for the magnetic recording medium.

30 [0033]

The magnetic coating solution preparing system 20 placed in the downstream of the sand mill dispersion system 18 is constituted by a liquid tank 82, a stirrer 84 with its leading end placed in the liquid tank 82, a liquid supplying pipe 86 from the liquid tank 82, a filter 88, and a pipe 90 from the filter 88. Also, in the liquid tank 82, a liquid C constituted by a lubricant and a solvent, and a liquid D being an additive solution (constituted by carbon black and an abrasive) are newly added.

[0034]

In the magnetic coating solution preparing system 20, the magnetic coating material is finally prepared, and is passed through the filter 88, whereby contaminants are removed, the magnetic coating material is supplied for a coating step.

[0035]

The production of the magnetic coating material using the production apparatus 10 for the magnetic coating material will now be described. For the ferromagnetic powder for use in the present invention, various kinds of materials may be used, but if the ferromagnetic powder is a hexagonal ferrite, a material with the plate diameter of 35 nm or less, and the plate ratio of 2 or greater may be used, and if the ferromagnetic powder is a ferromagnetic metal powder, a material with the major axis length of 60 nm or less, and the axis ratio of 2 or greater may be preferably used. For the particle size of this ferromagnetic powder, a material with the average primary particle volume of $10,000 \text{ nm}^3$ or smaller may suitably be used.

[0036]

In the liquid A, the solvent in which the ferromagnetic powder is immersed is preferably a solution containing a cyclohexanone. The content of cyclohexanone is preferably 30 to 100% by weight of the total amount of solvent. For the solution other than cyclohexanone, methyl ethyl ketone, toluene, butyl acetate or the like is preferably used.

[0037]

Dispersing the liquid A constituted by a ferromagnetic powder and a solvent by applying an ultrasonic wave thereto before processing by the production apparatus 10 for the magnetic coating material provides more effects. The dispersion processing by applying an ultrasonic wave may have any of a batch-type processing form and a flow-type processing form. In other words, the dispersion processing may have any form as long as the liquid concentration, and the frequency, the irradiation area, the number of circulations and the like in ultrasonic dispersion can be set so that cavities (voids) generated in ultrasonic dispersion

processing can be assigned in larger quantity and more uniformly to the ferromagnetic powder immersed in the solvent.

[0038]

The liquid concentration of the liquid A is preferably 5 to 80% by weight, more preferably 10 to 50% by weight, further preferably 25 to 50% by weight. The upper limit of the liquid concentration is defined by permeability, and the lower limit of the liquid concentration is defined by the effect of ultrasonic dispersion.

[0039]

The condition will be described when the ultrasonic dispersion processing for the unprocessed liquid A by the production apparatus 10 for the magnetic coating material is carried out by a batch processing. A frequency of 15 to 1000 kHz can suitably be employed as an ultrasonic frequency. A high frequency is preferable in terms of the number of generated cavities, while a low frequency is preferable in terms of explosive power of generated cavities. In this respect, by using ultrasonic dispersion processing of different frequencies in combination, the coagulated magnetic material can be dispersed more effectively.

[0040]

If ultrasonic dispersion processing is carried out with a single frequency, the magnetic material can be dispersed by spending a predetermined amount of time (power consumption) at a frequency of 20 to 40 kHz. If the frequency of 20 kHz is compared with the frequency of 40 kHz, the frequency of 40 kHz is more preferable in that the irradiation area is more likely to be increased, and a larger number of cavities in the liquid are generated and fractured. For the batch-type ultrasonic dispersion apparatus with the frequency of 40 kHz, a various kinds of commercially available ultrasonic cleaners and the like may be used. The manufacturer and the like are not specifically limited.

[0041]

When ultrasonic dispersion processing is carried out, it is preferable that the unprocessed liquid A is put in a closed container made of glass, plastic or the like having a diameter smaller than the ultrasonic irradiation area, and the container is placed on an ultrasonic irradiation part. Also, if the liquid A to be processed is put in a container having a diameter larger than the ultrasonic irradiation area, the liquid is more preferably stirred by a stirrer.

[0042]

The condition will be described when the ultrasonic dispersion processing for the unprocessed liquid A by the production apparatus 10 for the magnetic coating material is carried out by a flow (circulation) processing. The frequency of the commercially available ultrasonic dispersion apparatus for flow processing is generally around 20 kHz. Hence, it is preferable that the number of circulations of the liquid A is secured, and thereby the number of generated and fractured cavities in the liquid is secured to promote the dispersing of the coagulated magnetic material. Also, the processing is preferably carried out at a higher flow rate as a measure against settlement of the magnetic material.

[0043]

For the ultrasonic dispersion apparatus, for example, a flow-type ultrasonic dispersion apparatus (trade name: US-1200TCVP) manufactured by Nippon Seiki Co., Ltd. may be used. The specifications of this apparatus have been described above, and are thus not shown. This ultrasonic dispersion apparatus has an ultrasonic irradiation zone having a circular shape with the diameter of 50 mm, which is preferable in that a larger irradiation area can be provided.

[0044]

In the solution B supplying system 14 shown in Figure 1, the concentration of solution B of binder is preferably set so that it has a liquid viscosity of 10 Pa·s (100P) or lower, more preferably 1 Pa·s (10P) or lower, most preferably 0.1 Pa·s (1P) or lower by vismetron.

[0045]

The ratio of the binder of the magnetic material in the solution B when the liquid A is mixed with the solution B is preferably 0.5 to 30 parts by weight, more preferably 2 to 15 parts by weight of binder relative to 100 parts by weight of magnetic material. Also, in consideration of assurance of film strength, assurance of dispersion and so on, it is preferable that a necessary binder is added in midstream depending on the dispersion level in the sense that the dispersion efficiency can be improved.

[0046]

The speed at which the magnetic coating material is processed by the production apparatus 10 for the magnetic coating material varies depending on the apparatus size, the concentrations of liquids, the compositions of liquids and the like, but for example, the liquid A and the solution B can be mixed at a flow rate of 500 g/minute, respectively, in the inverted Y type pipe 30 corresponding to the inlet of the ultrasonic dispersion system 16 of the

production apparatus 10 for the magnetic coating material. In this case, as long as the inverted Y type pipe 30 has a structure described previously (the pipe volume of the straight part is 3 cm^3), the ultrasonic wave is applied when the time of 0.18 to 0.32 seconds passes (when the specific gravity of the mixture reaches 1 to 1.8 g/cm^3) after the liquid A and the solution B are mixed together.

[0047]

Various kinds of well known methods of production may be employed for production of the magnetic recording medium by the magnetic coating material obtained by the production apparatus 10 for the magnetic coating material. For example, for the method for coating the magnetic coating material, the roller coating method, the dip coating method, the fountain coating method and the like may be employed for the application type, and the air knife coating method, the blade coating method, the bar coating method and the like may be employed for the measurement method. Also, for the method of dealing with the application type and the measurement type in the same part, the extrusion coating method, the slide bead coating method, the curtain coating method and the like may be employed.

[0048]

The magnetic layer of the produced magnetic recording medium preferably has a thickness of 0.02 to $3 \mu\text{m}$, more preferably 0.02 to $0.2 \mu\text{m}$ in dry state. Also, the layer composition is preferably such that a nonmagnetic layer having mainly a nonmagnetic powder and a binder is provided between the magnetic layer and a nonmagnetic substrate. Particularly, the composition in which the magnetic layer is a thin layer has not only an advantage that a reduction in C/N in the shortwave range is prevented to improve the medium performance but also an advantage that productivity can be improved because the level of coating seams associated with the dispersing of the coagulated magnetic material can be reduced.

[0049]

The illustrative embodiment of the method for producing the magnetic recording medium according to the present invention has been described above, but the present invention is not limited to the above illustrative embodiment, and various kinds of aspects may be adopted.

[0050]

For example, three flow-type ultrasonic dispersion apparatuses 40, 60 and 62 are

placed in series in this illustrative embodiment, but only one ultrasonic dispersion apparatus having greater output may be placed, or multiple ultrasonic dispersion apparatuses each having small output may be placed.

[0051]

5 Also, as described previously, various kinds of devices exhibiting the same effect, such as an inverted T type pipe may be employed in place of the inverted Y type pipe 30.

[0052]

[Examples]

Examples of the present invention will now be described in contrast with

10 Comparative Examples. In each Example described below, the expression of "parts" means "parts by weight".

[0053]

Each Example described below employs a layer composition in which a nonmagnetic intermediate layer having mainly a nonmagnetic powder and a binder is provided between a
15 magnetic layer and a nonmagnetic substrate.

[0054]

In Example 1 as an Example of the present invention, a magnetic coating material prepared in such a manner that the liquid A constituted by a ferromagnetic powder and a solvent and the solution B of a binder are mixed together by applying an ultrasonic wave
20 thereto in the production apparatus 10 for the magnetic coating material having a configuration shown in Figure 1, and are thereafter subjected to dispersion processing is used.

[0055]

On the other hand, in Example 2 as a Comparative Example, a magnetic coating material prepared in such a manner that using as a ferromagnetic powder a barium ferrite
25 having a plate diameter of 26 nm and a plate ratio of 3, the ferromagnetic powder is made to contact a binder solution and kneaded by an open kneader to prepare a liquid, and thereafter the prepared liquid is subjected to dispersion processing in preparation of a magnetic liquid is used.

[0056]

30 In Example 3 as a Comparative Example, a magnetic coating material prepared in such a manner that unlike Example 1 (Example of the present invention), the liquid A constituted by a ferromagnetic powder and a solvent and the solution B of a binder are stirred

and mixed by a dissolver-type stirrer at a circumference speed of 18 m/second for 30 minutes and subjected to dispersion processing instead of carrying out prior ultrasonic dispersion mixing and flow-type ultrasonic dispersion processing is used.

[0057]

5 The compositions of Examples 1 to 3 will be described below with common aspects described collectively and different aspects described individually.

[0058]

(1) Compositions of Nonmagnetic Intermediate Layer (common in Examples 1 to 3)

	nonmagnetic powder α -Fe ₂ O ₃ :	80 parts
10	average major axis length:	0.1 μ m
	specific surface area based on BET method:	48 m ² /g
	pH 8, content of Fe ₂ O ₃ :	90 percents or greater
	DBP oil adsorption:	27 to 38 ml/100 g
	surface finishing agent: Al ₂ O ₃	
15	carbon black:	20 parts
	average primary particle size:	16 μ m
	DBP oil adsorption:	80 ml/100 g
	pH:	8.0
	specific surface area based on BET method:	250 m ² /g
20	volatile component:	1.5%
	vinyl chloride copolymer:	8 parts
	MR-110 manufactured by Zeon Corporation	
	polyester polyurethane resin:	4 parts
	neopentyl glycol / caprolactone polyol / MDI = 0.9/2.6/1	
25	containing 1×10^{-4} eq/g of SO ₃ Na base:	Tg 65°C
	phenylsulfone acid:	3 parts
	butyl stearate:	1 part
	stearic acid:	1 part
	methyl ethyl ketone:	150 parts
30	cyclohexanone:	100 parts

The coating material of the nonmagnetic intermediate layer described above was

prepared by kneading components other than stearic acid and butyl stearate by an open kneader, followed by subjecting the kneaded components to dispersion processing by a pin-type sand mill dispersion apparatus of lateral circulation type (2L type) packed with small-size zirconia beads (diameter of 0.5 mm) with the bead filling factor of 80%, at a pin point circumferential speed of 12 m/second, at a flow rate of 0.5 kg/minute and with dispersion retention time of 60 minutes.

[0059]

A liquid prepared by adding 3 parts of polyisocyanate to the dispersed liquid, further adding thereto 1 part of stearic acid and 1 part of butyl stearate, and dissolving them with methyl ethyl ketone and cyclohexanone (methyl ethyl ketone : cyclohexanone = 36 parts : 24 parts) was added and stirred to prepare a nonmagnetic coating solution with the solids content of 28% and the solvent ratio of methyl ethyl ketone : cyclohexanone = 6 : 4. The nonmagnetic coating solution was filtered using a filter having an average pore size of 1 μm and thereby conditioned.

[0060]

(2) Composition of Magnetic Layer (The magnetic liquid and the additive solution are presented. Others are not presented)

a) Additive Paste Liquid (additive solution) (common in Examples 1 to 3)

α -alumina (particle size 0.18 μm):	4.5 parts
carbon black (particle size 0.10 μm):	0.5 parts
MR 110:	0.45 parts
Cyclohexanone:	9.2 parts

The additive paste liquid had a composition of carbon black : alumina : MR 110 : cyclohexanone = 5 : 45 : 4.5 : 50.5, and this paste liquid was subjected to two-pass processing at a flow rate of 30 g/minute, apart from the magnetic material, using a flow-type ultrasonic dispersion apparatus (1200 W, the frequency was 20 kHz, the diameter of the surface of the irradiation part was 50 mm, the space between the irradiation part and the holder was 3 mm, the amplitude was 30 μm).

[0061]

b) Magnetic Liquid (different among Examples 1 to 3)
(Example 1)

	Ferromagnetic powder:	100 parts
	plate diameter:	26 nm
	plate ratio:	3
	average primary particle volume:	3805 nm ³
5	SBET:	60 m ² /g
	pH:	7.9
	Hc:	187856 A/m (2360 Oe)
	σ_s :	49 A·m ² /kg
	true specific gravity:	5.1 g/ml
10	apparent specific gravity:	0.7 g/ml
	MR 110:	10 parts
	methyl ethyl ketone:	20 parts
	cyclohexanone:	170 parts

For preparation of the magnetic coating solution of the Example, the components were blended so that the liquid A had a composition of ferromagnetic powder : cyclohexanone = 100 parts : 150 parts. As pre-stirring, 100 g of liquid A (mixture) was put in a cylindrical container with the inner diameter of 50 mm (flat bottom, thickness 2 mm, made of glass, height 100 mm, capped-type), and the cylindrical container containing the mixture was placed in an ultrasonic cleaner Model: BRANSONIC 220 manufactured by BRANSON Co., Ltd. (specifications: 125W, the diameter of irradiation surface of 50 mm and two oscillation parts, frequency 40 kHz) with water introduced therein to process the liquid A.

[0062]

The cylindrical container was placed just above the oscillation part of the ultrasonic cleaner, and ultrasonic processing was carried out with in one minute after immersion in a solvent (mixing). The amount of ultrasonic processing time was 30 minutes. Thereafter, it was put in the liquid tank 21 of the liquid A supplying system 12 of the production apparatus 10 for the magnetic coating material shown in Figure 1, and was stirred by the stirrer 22 and then left standing.

[0063]

Independently, as the solution B, a binder solution of MR110 : cyclohexanone : methyl ethyl ketone = 10 : 20 : 20 (solids content in liquid was 20%) prepared by the dissolver-type stirrer was put in the liquid tank 25 of the solution B supplying system 14 of the

production apparatus 10 for the magnetic coating material shown in Figure 1, and was stirred by the stirrer 26 and then left standing.

[0064]

The mixing of the liquid A and the solution B was carried out by applying an ultrasonic wave thereto after the liquid A was merged with the solution B by the inverted Y type pipe 30. In the ultrasonic dispersion system 16, the previously described Flow-type Ultrasonic Dispersion Apparatus (trade name: US-1200TCVP) manufactured by Nihon Seiki Co., Ltd. (specifications are not shown) was used as the flow-type ultrasonic dispersion apparatuses 40, 60 and 62.

[0065]

The inflow rates of the liquid A and the solution B into the inverted Y type pipe 30 were each 500 g/minute to carry out the mixing. The mixture leaving the ultrasonic dispersion apparatus 40 was further passed through the ultrasonic dispersion apparatuses 60 and 62 coupled in series.

[0066]

Then, in the sand mill dispersion system 18, the mixture was processed by a pin-type sand mill dispersion apparatus 78 of lateral circulation type (2L type). For the processing conditions, dispersion processing was carried out at a pin point circumferential speed of 10 m/second, at a flow rate of 0.5 kg/minute and with dispersion retention time of 30 minutes, with the dispersion apparatus packed with small-size zirconia beads (diameter of 0.5 mm) with the bead filling factor of 80%.

[0067]

(Example 2)

As Comparative Example, using as a ferromagnetic powder a barium ferrite having a plate diameter of 26 nm and a plate ratio of 3, the ferromagnetic powder was made to contact a binder solution kneaded by an open kneader to prepare a liquid, and thereafter the prepared liquid was subjected to dispersion processing in preparation of a magnetic liquid. The proportion of the ferromagnetic powder was same as that of Example 1.

[0068]

More specifically, the ferromagnetic powder, the binder, methyl ethyl ketone and cyclohexanone were kneaded by the open kneader, followed by subjecting the kneaded components to dispersion processing by a pin-type sand mill dispersion apparatus of lateral

circulation type (2L type) packed with small-size zirconia beads (diameter of 0.5 mm) with the bead filling factor of 80%, at a pin point circumferential speed of 10 m/second, at a flow rate of 0.5 kg/minute and with dispersion retention time of 30 minutes.

[0069]

5 (Example 3)

As Comparative Example, the liquid A constituted by a ferromagnetic powder and a solvent and the solution B of a binder were stirred and mixed by a dissolver-type stirrer at a circumference speed of 18 m/second for 30 minutes and subjected to dispersion processing, instead of carrying out prior ultrasonic dispersion mixing and flow-type ultrasonic dispersion processing. The proportion of the ferromagnetic powder was same as that of Example 1.

[0070]

The step of mixing the magnetic liquid of the Examples 1 to 4 and the previously described additive paste liquid to prepare a magnetic coating material in the magnetic coating solution preparing system 20 shown in Figure 1 will now be described.

15 [0071]

The magnetic coating solution and the additive paste liquid were put in the liquid tank 82 of the magnetic coating solution preparing system 20, and was mixed and stirred by the stirrer 84, and a solution with 0.5 parts of stearic acid and 1.5 parts of butyl stearate dissolved by 50 parts of methyl ethyl ketone and 30 parts of cyclohexanone was added and stirred to prepare a magnetic coating (magnetic coating material). The magnetic coating solution was filtered by the filter 88 having an average pore size of 1 μm and thereby conditioned.

[0072]

A magnetic tape as the magnetic recording medium was produced in the following step. As a nonmagnetic substrate, polyester naphthalate of which the roughness component strength was 0.03 nm^2 with the thickness of $5.2 \mu\text{m}$ and the wavelength of $4.3 \mu\text{m}$ in the roughness spectral of AFM was used.

25 [0073]

Simultaneous double layer coatings were provided on the substrate so that the post-dry thickness of the nonmagnetic layer coating solution was $1.5 \mu\text{m}$, and immediately thereafter, a magnetic layer with the post-dry thickness of $0.1 \mu\text{m}$ was formed thereon. When both the nonmagnetic layer and magnetic layer were still wetted, they were oriented by a

30

cobalt magnet having a magnetic force of 3000G and a solenoid having a magnetic force of 1500G and thereby dried, and were thereafter processed at a temperature of 85°C, under a linear pressure of 350 kg/cm and at a speed of 50 m/minute by a seven-stage calendar apparatus composed only of a metal roll, and the substrate was slit into a width of 6.35 mm, thereby producing a magnetic tape.

[0074]

The magnetic tapes of the Examples 1 to 3 were evaluated for the following two items. That is, the items are the number of masses and the cluster size.

[0075]

The number of masses was examined by counting the number of flecked masses per predetermined area using an optical microscope. Numbers of masses equivalent to 8 visual fields in the 500 times visual field were summed to determine the number of masses. The area equivalent to 8 visual fields in the 500 times visual field corresponds to 0.1768 mm².

[0076]

In Example 1 (Example of the present invention), the number of masses was 0. On the other hand, the numbers of masses were 140 and 0 in Examples 2 and 3 as Comparative Examples, respectively.

[0077]

The cluster size was measured by MFM (magnetic force microscope). In Example 1 (Example of the present invention), the cluster size was 5,800 nm². On the other hand, in Examples 2 and 3 as Comparative Examples 2 and 3, the cluster sizes were 29,000 nm² and 10,000 nm² respectively.

[0078]

If compared the Example of the present invention with Comparative Examples, it can be understood that in Example 1 (Example of the present invention), the number of coagulated flecked masses when observing the surface of the magnetic layer by the optical microscope is small and the magnetized cluster size by MFM is small compared to Example 2 (Comparative Example), and therefore the effect of the present invention can be ascertained.

[0079]

It can be understood that in Example 3 (Comparative Example), the number of masses is small and the magnetized cluster size by MFM is also small compared to Example 2 (Comparative Example), but it can also be understood that Example 3 is apparently inferior to

the Example of the present invention.

[0080]

[Advantage of the Invention]

As described above, according to the present invention, the liquid A constituted by a
5 ferromagnetic powder and a solvent and the solution B of a binder can be mixed together by
applying the ultrasonic wave thereto, thus making it possible to obtain a ferromagnetic powder
solution in which coagulated particles of the ferromagnetic powder can be dispersed, the
ferromagnetic powder can be prevented from coagulating, and the binder is uniformly
adsorbed. Consequently, a magnetic coating material suitable for a low-noise high-density
10 coating-type magnetic recording medium can be obtained.

[Brief Description of the Drawings]

[Figure 1]


Figure 1 is an overall block diagram of a production apparatus for a magnetic coating
material for use according to an embodiment of the present invention; and

15 [Figure 2]


Figure 2 is a detailed sectional view of an ultrasonic dispersion apparatus for use in
an ultrasonic dispersion system.

[Description of the Symbols]

- 10 production apparatus for magnetic coating material
- 20 12 liquid A supplying system
- 14 solution B supplying system
- 16 ultrasonic dispersion system
- 18 sand mill dispersion system
- 20 magnetic coating solution preparing system



[Fig. 2]



[Title of the Document] Abstract

[Abstract]

[Problem to be Solved]

To provide a low-noise high-density coating-type magnetic recording medium.

5 [Solution]

A method for producing a magnetic recording medium having a nonmagnetic substrate coated with a magnetic coating material containing a ferromagnetic powder and a binder. The magnetic coating material contains a liquid A constituted by the ferromagnetic powder and a solvent, and a solution B of the binder; and the liquid A and the solution B are
10 mixed together by applying an ultrasonic wave thereto, and are thereafter subjected to dispersion processing.

[Selected Drawing] Figure 1